



- Backing:** 1.7 mil highly-breathable copolyester film
- Adhesive:** Medical-grade acrylic (M103)
- Liner:** 60lb semi-bleached kraft, silicone treated on one side

Applications

- Wound care
- Transdermal overlay
- Surgical dressings
- Surgical incise

Features

Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> • Copolyester Film Backing • Medical-Grade Acrylic • 60lb Release Liner | <ul style="list-style-type: none"> • High breathability supports extended wear and patient comfort • Conformable and flexible • Non-reflective to prevent glare • Excellent performance in adhesion to both skin and other surfaces • Easy to die-cut and convert |
|---|--|

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	6.3 mils	0.160 mm	PSTC 133
Adhesive Thickness	1.4 mils	0.036 mm	PSTC 133
Carrier Thickness	1.7 mils	0.043 mm	PSTC 133
Liner Thickness	3.2 mils	0.081 mm	PSTC 133
Adhesion to Steel	50 oz/in	5.47 N/cm	PSTC 101 Mod
Adhesion to HDPE	45 oz/in	4.92 N/cm	PSTC 101 Mod
Liner Release	20 g/in	0.08 N/cm	ASTM D-5375
MVTR	1690 g/m ² /24 hrs		ASTM F-1249

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.