


Single-Coated Foam Tape



- Backing:** 1/32" white, crosslinked polyethylene foam
- Adhesive:** Acrylic (M110)
- Liner:** 2 mil polyester film, silicone coated on one side

Applications

- Electrodes: ECG, EKG, TENS
- AED defibrillator pads
- Medical device mounting
- Transdermal delivery system

Features

- Polyethylene Foam Backing
- Acrylic Adhesive
- Polyester Film Liner

Benefits

- Soft and flexible for maximum patient comfort
- Conformable and easily adapts to medical devices and body contours
- Aggressive adhesive designed for extended wear applications
- Removes cleanly without causing trauma
- Highly resistant to perspiration-borne moisture
- Excellent lay flat and dimensional stability
- Easily die-cut

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	36.2 mils	0.919 mm	PSTC 133
Adhesive Thickness	3.0 mils	0.076 mm	PSTC 133
Liner Thickness	31.2 mils	0.792 mm	PSTC 133
Liner Thickness	2.0 mils	0.051 mm	PSTC 133
Adhesion to Steel	100 oz/in	10.94 N/cm	PSTC 101 Mod
Liner Release	40 g/in	0.15 N/cm	ASTM D-5375

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.